



MYK LATICRETE

Tile & Stone Installation Solutions

LATICRETE®111 Crete Filler Powder



PRODUCT DESCRIPTION

LATICRETE 111 Crete Filler Powder is a factory prepared blend of carefully selected raw materials, portland Cement and graded aggregates. Designed for use with LATICRETE 73 Latex Admix to produce a High Strength Adhesive for Ceramic Tile and Stone installation that meets and exceeds the requirements of international standards.

Application:

For the installation of ceramic tile and stone over cement and masonry type surfaces. Applications include: Interior and exterior, wet and dry areas, walls, floors and ceilings. New and remodel construction, residential or commercial applications.

Advantages

- High strength, flexible, shock & impact resistant
- Versatile- wet and dry areas, walls, floor & ceilings
- Easy to use
- Economical – saves time and money

Suitable Substrates

- Concrete
- Ceramic Tile & Stones
- Concrete Masonry
- Brick Masonry
- Gypsum Wallboard (Interior Only)
- Cement Mortar Beds
- Cement Backer Board
- Cement Plaster
- Cement Terrazzo

Packaging

20 kg bag

Colour: Grey and White

Coverage

Approx 55 - 60 sft per 20 kg bag using 1/4" x 1/4" (6 x 6 mm) square notch trowel.

Shelf Life - Factory sealed containers of this product are guaranteed to be of first quality for one (1) year* if stored off the ground in a dry area.

*High humidity will reduce the shelf life of bagged product.

Limitations

Use LATAPOXY® 300 Epoxy Adhesive for installing green marble or water sensitive natural stone and agglomerates. Use a white thin set mortar when installing white or light colored natural stones.

Adhesives/mastics, mortars and grouts for ceramic tile, pavers, brick and stone are not replacements for waterproof membranes. When a waterproof membrane is required, use a LATICRETE Waterproof Membrane

Note: Surfaces must be structurally sound, stable and rigid enough to support ceramic/stone tile, thin brick and similar finishes. Substrate deflection under all live, dead and impact loads, including concentrated loads, must not exceed L/360 for thin bed ceramic tile/brick installations or L/480 for thin bed stone installations where L=span length.

Cautions

During cold weather, protect finished work from traffic until fully cured.

Contains Portland cement and silica sand. May irritate eyes and skin. Avoid contact with eyes or prolonged contact with skin. In case of contact, flush thoroughly with water.

Do not take internally. Silica sand may cause cancer or serious lung problems. Avoid breathing dust. Wear a respirator in dusty areas.

Keep out of reach of children.

TECHNICAL DATA

Applicable Standards

ANSI A118.4-1999

Performance Properties

LATICRETE 111 mixed with LATICRETE 73 Latex Crete admix

Test	Test Method	Results
Shear Bond, Porcelain Tile, 28 day cure	ANSI A118.4-1999; F-5.2.4	275 psi (1.8 MPa)
Shear Bond Porcelain Tile Water immersion	ANSI A118.4-1999; F-5.2.3	200 psi (1.37 Mpa)
Compressive Strength	ANSI A118.4-1999; F-6	3000 psi (20.6 MPa)

Working Properties

LATICRETE 111 mixed with LATICRETE 73 Crete admix (21° C)

Open Time	30 minutes
Pot Life	5 hours
Time to Heavy Traffic	24 hours
Wet Density	1800 kg/ m3

Specifications subject to change without notification. Results shown are typical but reflect test procedures used. Actual field performance will depend on installation methods

Performance Properties

LATICRETE 111 mixed with LATICRETE 4237 Latex Thin-set Mortar Additive

Test	Test Method	Results
Shear Bond, Porcelain Tile, 28 day cure	ANSI A118.4-1999; F-5.2.4	350 psi (2.4 MPa)
Shear Bond Porcelain Tile Water immersion	ANSI A118.4-1999, A-5.2.3	210 psi (1.4 Mpa)
Compressive Strength	ANSI A118.4-1999; F-6.1	4000 psi (27.5 MPa)

Working Properties

LATICRETE 111 mixed with LATICRETE 4237 Latex Thin-set Mortar Additive (21° C)

Open Time	30 minutes
Pot Life	5 hours
Time to Heavy Traffic	24 hours
Wet Density	1780 kg/ m3

Specifications subject to change without notification. Results shown are typical but reflect test procedures used. Actual field performance will depend on installation methods

INSTALLATION

Surface Preparation

All Surfaces should be between 40°F(4°C) and 90°F(32°C) and Do not set tile when surface temperature is below freezing or from all dirt, oil, grease, loose peeling paint, laitance concrete sealers or curing compounds. Rough or uneven concrete surfaces should be made smooth when substrate is frozen. LATICRETE Latex Portland Cement underlayment to provide a wood float (or better) finish. Dry, dusty concrete slabs or masonry should be dampened and excess water swept off.

Installation may be made on a damp surface. Note: Latex Portland Cement Mortars do not require a minimum cure time for concrete slabs. All slabs must be plumb and true to within 1/4" (6mm) in 10ft(3m). Expansion joints shall be provided through the tile work from all construction or expansion joints in the substrate. Follow ANSI Specification AN-3.8 "

Requirements for Expansion Joints" or TCA Detail EJ171-98 "Expansion Joints". Do not cover expansion joints with mortar. Cement Backer Board: follow TCA installation detail W244.

Mixing

Stir LATICRETE admix thoroughly before use.

Place LATICRETE 73 latex admix into a clean pail. Add LATICRETE 111 Crete filler powder. Use approximately 5-6L of latex admix for 20 kg of powder.

Mix by hand or with a slow speed mixer to a smooth, trowelable consistency. Allow adhesive to slake for 5-10 minutes. Adjust consistency if necessary. Remix and apply with the proper sized notched trowel.

Application

Apply adhesive to the substrate with the flat side of the trowel, pressing firmly to work into surface. Comb on additional adhesive with the notched side. Use the proper sized notched trowel to insure full bedding of the tile. Spread as much adhesive as can be covered with tile in 10 minutes. Back butter large tiles (> 12"x12") to provide full bedding and firm support. Place tiles into wet, sticky adhesive and beat in using a beating block and rubber mallet to imbed tile and adjust level. Check adhesive for complete coverage by periodically removing a tile and inspecting bedding adhesive transfer onto back of tile. If adhesive is skinned over (not sticky), remove and replace with fresh adhesive.

Grouting

Grout installation after a minimum of 24 hours curing time at 70° F(21° C). Grout with LATICRETE LATICRETE Sanded or Unsanded Grout mixed with LATICRETE 282 Grout Admix . For maximum stain resistance use LATAPOXY SP-100 Stainfree Grout.

Cold Weather Note: The setting of Portland cement adhesives and grouts are retarded by low temperatures. Protect finished work for an extended period when installing in cold weather. For faster setting adhesive use LATICRETE 73 Rapid with LATICRETE 111

Do not set tile when surface temperature is below freezing or when substrate is frozen.

Hot Weather Note: The evaporation of moisture in Portland cement adhesives and grouts is accelerated by hot, dry conditions. Apply to dampened surfaces and protect freshly spread adhesive and finished work when installing in temperatures over 95°F (35°C).

Cleaning

Clean tools and tile work with water while adhesive is fresh.

AVAILABILITY AND COST

Availability

LATICRETE and LATAPOXY ® materials are available worldwide.

For distributor information:

Telephone: +91-40-30413100

FAX: +91-40-23378784

e-mail: contact@myklaticrete.com

Cost

Contact a LATICRETE Distributor in your area.

MAINTENANCE

LATICRETE and LATAPOXY grouts require routine cleaning with a neutral pH soap and water. All other LATICRETE and LATAPOXY materials require no maintenance but installation

performance and durability may depend on properly maintaining products supplied by other manufacturers.

WARRANTY

MYK LATICRETE India Pvt Ltd warrants that LATICRETE ® 111 Crete filler powder is free from manufacturing defects and will not break down, deteriorate or disintegrate under normal usage for a period of one (1) year from date of purchase subject to the terms and conditions stated in LATICRETE Product Warranty

TECHNICAL SERVICES

Technical assistance

Information is available by calling the LATICRETE Technical Service at:

Telephone: +91-40-30413100

FAX: +91-40-23378784

e-mail: contact@myklaticrete.com

MYK Laticrete India Pvt Ltd.

6-3-569/2, First Floor, Kamadhenu Complex

Rockdale Compound, Somajiguda

Hyderabad – 500082 (A.P)

Tel: +91-40-30413100

Fax: +91-40-23378784

e-mail: contact@myklaticrete.com

Website :-www.myklaticrete.com