



SPECIFICATION FOR INSTALLATION OF GLASS MOSAIC TILES ON PLYWOOD WALL SURFACE BY THINSET METHOD

a) TILE FIXING:

Fixing glass mosaic tile on plywood wall surface with Laticrete 290 premium thin set adhesive mixed with Laticrete 333 Super flexible latex admix. The thickness of adhesive shall be 2mm

The mixing ratio shall be as follows

20kg bag Laticrete 290 : 6.5 ltr Laticrete 333

The plywood on wall should be of minimum 5/8" (15mm) exterior grade.

The maximum deflection under all live, dead and impact loads shall not exceed the industry standard of L/360 for a ceramic tile and L/480 for natural stone.

The plywood shall be strong enough to carry the weight of tile

The adhesive shall be applied using Laticrete square notch trowel as supplied by the company

For detailed information on surface preparation refer to Laticrete Technical data sheet 152

For detailed installation and laying procedure follow Laticrete Method Statement.

Laticrete products supplied shall be as Manufactured by MYK Laticrete India Pvt Ltd

Performance Properties:

Latex fortified thinset adhesive - Laticrete 290 thinset adhesive powder + Laticrete 333 latex admix

Test	ANSI 118.1	Result
Initial Set	> 6 hours	4 hours
Final Set	9 – 15 hour	6 hour 30 min
28 day shear bond	> 200 psi	280 psi
28 day compressive	> 2500 psi	4100 psi

Product Standard : ANSI 118.1 - 1999

b) JOINT FILLING:

Providing and fixing spacer between tiles as per architecture requirement and grouting the same with Laticrete Tile Grout mixed with Laticrete 1776 Grout admix plus.

For joints 1-3mm, use Laticrete Unsanded grout (600 series) mixed with Laticrete 1776.

For joints 3-12mm, use Laticrete Sanded grout (500 series) mixed with Laticrete 1776.

Mixing ratio shall be as follows:

10kg bag Laticrete Unsanded grout : 3.75ltr Laticrete 1776 grout admix plus.

10kg bag Laticrete Sanded grout : 1.75ltr Laticrete 1776 grout admix plus.

For detailed installation and laying procedure follow Laticrete Method Statement.

Laticrete products supplied shall be as Manufactured by Laticrete India Pvt Ltd

Performance Properties:

Laticrete tile grout – Laticrete 600 series unsanded grout + Laticrete 1776 grout admix plus.

Test	ANSI 118.6	Result
Linear shrinkage 7 days	< 0.10%	<0.1%
Flexural strength 7 days	400 psi	800 psi
Tensile strength 28 days	350 psi	400 psi
Compressive strength 28 days	3000 psi	3050 psi

Product Standard : ANSI A118.6 -1999**Performance Properties:**

Laticrete tile grout – Laticrete 500 series Sanded grout + Laticrete 1776 grout admix plus.

Test	ANSI 118.6	Result
Linear shrinkage 7 days	< 0.10%	<0.1%
Flexural strength 7 days	350psi	700 psi
Tensile strength 28 days	350psi	350 psi
Compressive strength 28 days	3500psi	3650 psi

Product Standard : ANSI A118.6 –1992