



SPECIFICATION FOR INSTALLATION OF CLAY TILES ON EXTERNAL WALL BY THIN SET METHOD

a) ADHESIVE:

Fixing clay tile on external wall with Laticrete 111 crete filler powder mixed with Laticrete 73 latex admix. The thickness of adhesive shall be based on the tile size

Tile size upto 300X300mm - 3mm adhesive thickness

Tile size 450X450mm – 4.5mm adhesive thickness

Tile size 600X600mm – 6.0mm adhesive thickness

Tile size 900X900mm – 7.5mm adhesive thickness

Tile size > 900X900mm – 9.0mm adhesive thickness

The mixing ratio shall be as follows

20kg bag Laticrete 111 : 5.5 ltr Laticrete 73

The plaster applied over the wall shall be strong, confirm to good design and capable of carrying out the weight of the tile, further the plaster shall be free of dirt, dust and level and true within 3mm in 2.5m.

The adhesive shall be applied using Laticrete square notch trowel as supplied by the company

For detailed installation and laying procedure follow Laticrete Method Statement.

Laticrete products supplied shall be as Manufactured by Laticrete India Pvt Ltd

Performance Properties:

Latex fortified thinset adhesive - Laticrete 111 crete filler powder + Laticrete 73 Crete admix

Test	ANSI 118.4	Result
Initial Set	>6 hr	7 hr 30 min
Final Set	9 – 15 hr	9 hr 30 min
28 day shear bond	200 psi	275 psi
28 day compressive	2500 psi	3000 psi

Product Standard : ANSI A118.4-1999

b) JOINT FILLING:

Providing and fixing spacer between tiles as per architecture requirement and grouting the same with Laticrete Tile Grout mixed with Laticrete 1776 Grout admix plus.

For joints 1-3mm, use Laticrete Unsanded grout (600 series) mixed with Laticrete 1776.

For joints 3-12mm, use Laticrete Sanded grout (500 series) mixed with Laticrete 1776.

Mixing ratio shall be as follows:

10kg bag Laticrete Unsanded grout : 3.75ltr Laticrete 1776 grout admix plus.

10kg bag Laticrete Sanded grout : 1.75ltr Laticrete 1776 grout admix plus.

For detailed installation and laying procedure follow Laticrete Method Statement.

Laticrete products supplied shall be as Manufactured by MYK Laticrete India Pvt Ltd

Performance Properties:

Laticrete tile grout – Laticrete 600 series unsanded grout + Laticrete 1776 grout admix plus.

Test	ANSI 118.6	Result
Linear shrinkage 7 days	< 0.10%	<0.1%
Flexural strength 7 days	400 psi	800 psi
Tensile strength 28 days	350 psi	400 psi
Compressive strength 28 days	3000 psi	3050 psi

Product Standard : ANSI A118.6 -1999

Performance Properties:

Laticrete tile grout – Laticrete 500 series Sanded grout + Laticrete 1776 grout admix plus.

Test	ANSI 118.6	Result
Linear shrinkage 7 days	< 0.10%	<0.1%
Flexural strength 7 days	350psi	700 psi
Tensile strength 28 days	350psi	350 psi
Compressive strength 28 days	3500psi	3650 psi

Product Standard : ANSI A118.6 -1992

c) SEALER:

Providing and sealing the clay tile with Laticrete Latamiracle 511 Impregnator. The clay tile shall be clean, free of impurities and in dry state.

The sealer shall be applied using a brush, towel or spray.

For detailed installation and laying procedure follow Laticrete method statement

Laticrete products supplied shall be as manufactured by MYK Laticrete India Pvt. Ltd.