




## LATICRETE® 226 Thick Bed Mortar



### PRODUCT DESCRIPTION

LATICRETE 226 Thick Bed Mortar is a factory Prepared blend of carefully selected raw materials, Portland cement and graded aggregates. Designed for use with LATICRETE 3642 Latex Concentrate to produce high strength latex fortified Thick bed adhesive, screeds and plaster that meet and exceed the requirements of National and International Standards.

### Application

For interior and exterior use for preparing thick bed adhesive, cement plasters and Screeds.

### Advantages

- High Strength
- Flexible, shock & impact resistant
- Improved adhesion to vitrified tiles
- improved bond strength, compressive & tensile strength
- easy to use
- fast & economical

### Suitable Substrates

(When mixed with LATICRETE 3642 Latex Concentrate)

- Concrete
- Cement Mortar Beds
- Concrete Masonry
- Cement Plaster
- Brick Masonry
- Cement Terrazzo

**Packaging** - 50 kg bag

Thickness	L226	L3642	Water	Coverage
12 mm	50 kg	1.25 ltr	3.75 ltr	25 sft
25 mm	50 kg	1.25 ltr	3.75 ltr	12 sft
35 mm	50 kg	1 ltr	4 ltr	8 sft
50 mm	50 kg	0.83 ltr	4.17 ltr	5 sft

**Colour:** Grey and White

### Coverage

Coverage will be based on following mix design

### Shelf Life

Factory sealed containers of this product are guaranteed to be of first quality for one (1) year\* if stored off the ground in a dry area.

\*High humidity will reduce the shelf life of bagged product

### Limitations

- Use LATAPOXY® 300 Epoxy Adhesive for installing green marble or water sensitive natural stone and agglomerates.
- Adhesives/mastics, mortars and grouts for ceramic tile, pavers, brick and stone are not replacements for waterproof membranes. When a waterproof membrane is required, use a LATICRETE Waterproof Membrane

### Cautions

- During cold weather, protect finished work from traffic until fully cured.
- Contains Portland cement and silica sand. May irritate eyes and skin. Avoid contact with eyes or prolonged contact with skin. In case of contact, flush thoroughly with water.
- Do not take internally. Silica sand may cause cancer or serious lung problems. Avoid breathing dust. Wear a respirator in dusty areas.
- Keep out of reach of children

### TECHNICAL DATA

#### Applicable Standard

- Conforms to ANSI A-118.4-1992: Latex Portland Cement Mortar (When mixed with LATICRETE 3642 latex Concentrate).

### Performance Properties

LATICRETE 226 mixed with LATICRETE 3642 Latex Concentrate

Test	Results
Compressive strength	3500 psi (24.1 Mpa)
Flexural Strength	1500 psi (10.3 Mpa)
Tensile strength	400 psi (2.7 Mpa)

### Working Properties

LATICRETE 226 mixed with LATICRETE 3642 Latex Concentrate (70°F (21°C))

Pot Life	1 hour
Time to Foot Traffic	24 hours
Time to Heavy Traffic	72 hours
Wet Density	1760 kg/m <sup>3</sup>

Specifications subject to change without notification. Results shown are typical but reflect test procedures used. Actual field performance will depend on installation methods and site conditions.

## INSTALLATION

### Surface Preparation

All surfaces should be between 40 °F(4 °C) and 90 °F(32 °C) and structurally sound, clean and free of all dirt, oil, grease, loose peeling paint, concrete sealers or curing compounds. Rough or uneven concrete surfaces should be made smooth with LATICRETE Latex Portland Cement under layment to provide a wood float (or better) finish. Dry, dusty concrete slabs or masonry should be dampened and excess water swept off. Installation may be made on a damp surface. All slabs must be plumb and true to within ¼”(6mm) in 10 ft(3m). Expansion joints shall be provided through the tile work from all construction or expansion joints in the substrate. Follow ANSI Specification AN-3.8 “Requirements for Expansion Joints” or TCA Detail EJ171 “Expansion Joints”. Do not cover expansion joints with mortar. Glass Mesh Mortar Unit: follow TCA installation detail W244. in temperatures over 95°F (35°C).

*Mixing* – Stir Laticrete admix thoroughly before use

Thick bed adhesive

Use approx. 50kg of Laticrete 226 thick bed adhesive mortar with 1 ltr of Laticrete 3642 & 4 ltr of potable water. Mix by hand or with a slow speed mixer to semi dry consistency.

### Application

#### Thick bed adhesive

Before placing mortar, apply a slurry bond coat made from Laticrete 3642 latex concentrate pre diluted with water 1:1 and mix with cement & sand 1:1

While the slurry bond coat is wet spread mortar & compact well.

For placing tiles apply another slurry bond coat over the mortar bed & install tiles. The tiles shall be placed & beaten in the mortar while the slurry bond coat is wet and sticky.

### Floor Screeds

Before placing mortar, apply a bonding slurry of LATICRETE 3642 pre diluted with water 1:1 and cement: sand 1:1 to the mortar

While the bonding slurry is wet spread the mortar and compact well.

### Plaster

Plumb, square and true wall with applications of mortar. Level, fill and patch block with site mix mortar or LATICRETE 226 Thick Bed Mortar Mix gauged with pre-diluted LATICRETE 3642.

Plasters made with site mix may slump if applied in more than 6mm thickness. Plasters made with LATICRETE 226 can be applied in thicknesses as great as 25 mm without the plaster slumping.

### Cleaning

Clean tools and tile work with water while mortar is fresh.

## AVAILABILITY AND COST

### Availability

LATICRETE and LATAPOXY ® materials are available worldwide.

For distributor information:

Telephone: +91-40-30413100

FAX: +91-40-23378784

e-mail: [contact@myklaticrete.com](mailto:contact@myklaticrete.com)

### Cost

Contact a LATICRETE Distributor in your area.

## MAINTENANCE

LATICRETE and LATAPOXY grouts require routine cleaning with a neutral pH soap and water. All other LATICRETE and LATAPOXY materials require no maintenance but installation performance and durability may depend on properly maintaining products supplied by other manufacturers.

## WARRANTY

MYK LATICRETE India Pvt Ltd warrants that LATICRETE ® 226

Thick bed mortar is free from manufacturing defects and will not break down, deteriorate or disintegrate under normal usage for a period of one (1) year from date of purchase subject to the terms and conditions stated in LATICRETE Product Warranty

## TECHNICAL SERVICES

### Technical assistance

Information is available by calling the LATICRETE Technical Service at:

Telephone: +91-40-30413100

FAX: +91-40-23378784

e-mail: [contact@myklaticrete.com](mailto:contact@myklaticrete.com)

**MYK Laticrete India Pvt Ltd.**

6-3-569/2, First Floor, Kamadhenu Complex

Rockdale Compound, Somajiguda

Hyderabad – 500082 (A.P)

Tel: +91-40-30413100

Fax: +91-40-23378784

e-mail: [contact@myklaticrete.com](mailto:contact@myklaticrete.com)

Website: [www.myklaticrete.com](http://www.myklaticrete.com)