



MYK LATICRETE® LATAFINISH Wall Putty

PRODUCT NAME

MYK LATICRETE ® LATAFINISH Wall Putty



PRODUCT DESCRIPTION

LATAFINISH Wall Putty is made of White cement, Polymers, Biocides, powder to be mixed with water at the time of application.

Application

- Designed for interior and exteriors surfaces.
- To make uneven surfaces to even and smooth surfaces.

Advantages

- Easy to Apply.
- Water Resistance
- Anti fungal Resistance
- Good Compressive Strength.
- Good Tensile Strength.
- Increase the Paint Coverage.

Packaging – 20 kg bag

Colour: White

Coverage

Approx 18 to 20 sft per kg for 2 coats with maximum thickness of 1.5 mm

Shelf Life - Factory sealed containers of this product are guaranteed to be of first quality for 8 months * if stored off the ground in a dry area. *High humidity will reduce the shelf life of bagged product.

Limitations

- Do not directly apply on the fungus, moss affected areas.
 - Do not apply directly on the dust, loosely bonded particles, oil, Grease etc affected surfaces.
- Note: Surfaces must be two coated cement sand smooth plaster, structurally sound and stable.

Cautions

- Contains Portland cement and silica. May irritate eyes and skin. Avoid contact with eyes or prolonged contact with skin. In case of contact, flush thoroughly with water.
- Do not take internally. Avoid breathing dust.
- Wear a respirator in dusty areas.
- Keep out of reach of children.

Applicable Standard

Performance Properties

Test	Specification	Results
Tensile 28 day cure	> 0.8 Mpa	> 1.2 Mpa
Compressive Strength	7 to 12 Mpa	> 8 Mpa
Initial Set	< 360 minutes	240 Minutes
Final Set	< 500 Minutes	390 Minutes
Water Retentivity @	> 95	NA

24 Hrs. - %		
Pot Life	NA	3 – 4 hours at RT.

Specifications subject to change without notification. Results shown are typical but reflect test procedures used. Actual field performance will depend on surface, climatic, site conditions etc.

MYK Laticrete India Pvt Ltd.

6-3-569/2, First Floor, Kamadhenu Complex
 Rockdale Compound, Somajiguda
 Hyderabad – 500082 (A.P)
 Tel: +91-40-30413100
 Fax: +91-40-23378784
 e-mail: contact@myklaticrete.com
 Website: www.myklaticrete.com

5. Mixing

Place clean, potable water into a clean pail. Add LATA Finish Powder. Use approximately 6 to 7 L of water for 20 kg of powder. i.e. Water to Powder ratio is 30 % to 35 %.

Mix with a slow speed mixer to a smooth, trowelable consistency and free from lumps. Allow adhesive to slake for 5-10 minutes. Adjust consistency if necessary. Remix and apply with the proper sized putty blades.

Application

Apply two coats of the above paste on to the substrate with the putty blades. Ensure that the second coat application should be done when the first coat is totally dried. Note that the total thickness of two coats is 1.5 mm.

Cleaning

Clean tools with water while plaster is fresh.

6. AVAILABILITY AND COST

Availability

LATICRETE and LATAPOXY® materials are available worldwide.

For distributor information:

Telephone: +91-40-30413100

FAX: +91-40-23378784

e-mail: contact@myklaticrete.com

7. TECHNICAL SERVICES

Technical assistance

Information is available by calling the LATICRETE Technical Service at:

Telephone: +91-40-30413100

FAX: +91-40-23378784

e-mail: contact@myklaticrete.com